

Product Data Sheet
 Edition 04,2009.
 Identification no. 8.1.005
 Version No. 06
 Sikafloor® 2530 New

Sikafloor® 2530W New

Water Dispersed, Colored Floor Sealer

Description Sikafloor 2530W New is a high-performance colored, two-component dispersion based on epoxy resin.

Uses For the production of colored sealing coats for light and medium exposure. On concrete, cement screed, epoxy mortar fiber cement boards, e.g. in production and storage halls, show rooms, garages, wet rooms, civil defense facilities. As deicing salt protection on tunnel walls and galleries not exposed to weathering.

- Advantages**
- Easy application
 - Good chemical and abrasion resistance
 - Visible end of pot-life
 - Fast curing
 - Good hiding properties for most shades
 - Water vapour permeable
 - Excellent carbonation barrier
 - Resistant to mechanical cleaning
 - Odorless and fungus resistant
 - Solvent free

Product Data

Colour shades *Standard Colours:* Ral 9010
 Ral 6011 (Reseda Green)
 Ral 7032 (Pebble Grey)

Minimum quantities of order will be required for other colour shades (depending on its availability, see Sikafloor colour chart)

Packaging 10 kg per set (component A + B)
 Component A : 7.0 kg pail
 Component B : 3.0 kg pail

Storage Dry, cool, shaded place (storage temperature from +5°C to +30°C)

Shelf life Min. 12 months if stored properly in unopened, original packaging



Technical Data

Density Approx. 1.22 kg/ltr (Comp. A + B)

Solid content Approx. 55% (DIN 53216)

Mixing ratio Component A : B = 7 : 3 (parts by weight)
Component A : B = 2 : 1 (parts by volume)

Consumption 0.15 - 0.20 kg/m² per coat

Pot life	+10°C	+20°C	+30°C
Sikafloor 2530 New *	~ 2 hours	~ 1.5 hours	~ 30 min.

* in 10-kg units

Waiting time	+10°C	+20°C	+30°C
Waiting time between coats			
Minimum	2 days	15 hours	10 hours
Maximum	7 days	5 days	3 days
Ready for foot traffic	2 days	15 hours	10 hours
Lightly serviceable	5 days	3 days	2 days
Fully serviceable	10 days	7 days	5 days

In case of a relative air humidity of 75% the waiting time for Sikafloor 2530W New is increased by 24 hours

Mechanical resistance (14-days / 23 °C) Abrasion resistance approx. 65 mg as per Taber Abraser, disk CS10, 1000g/1000 revolutions.

Chemical resistance Resistant to water, sea water, sodium chloride solution, ammonium sulfate 10%, calcium chloride 10%, ammonia 5%, sodium hydroxide 50%, glycerine, petrol, diesel, fuel oil, lubricants, disinfectants, fruit juice and a number of industrial chemicals.

For specific chemicals please contact our Technical Service Department.

Thermal resistance Dry heat : up to approx. +100°C
Damp heat : up to +80°C (temporary exposure, steam cleaning etc)

Application

Substrate condition The substrates must be of sufficient strength (compressive strength minimum 25 N/mm²). The surface should be level, solid and dry as well as free from loose, friable particles and oil, etc. The pull-off strength should be above 1.5 N/mm².

Surface preparation A sound and clean substrate is of utmost importance, in particular as this flooring system is a thin layer system, hence loads applied to the floor are transmitted to the substrate.

Cavities or defects in the surface should be levelled with suitable material (e.g. using Sikagard 75 Epocem) prior to treatment.

Mixing Prior to mixing stir component A well. Mix component A+B intensively in the recommended mixing ratio by means of an electric power stirrer (maximum 500 rpm).

Mixing time is minimum 3 minutes but it may take longer until a homogeneous mixture is achieved. Fill mixed material into a clean container and mix again shortly.

Application method	<p>In order to achieve a uniform wetting of the substrate, apply material by means of brush, distemper brush or roller.</p> <p>Irregular spreading of material and layer thickness may cause differences in the degree of gloss.</p> <p>During application and curing adequate ventilation must be provided, especially at temperatures below +13°C, in order to prevent curing and drying malfunctions.</p>
Cleaning	Clean the application tools after use with soap water in order to remove remnants of resin and rinse again with clean water.
Overworkability	After thorough cleaning and grinding/sanding Sikafloor 2530 New can be overworked with itself.
Notes on application /Limits	<ul style="list-style-type: none"> ■ Substrate moisture content < 5 % ■ Cementitious substrate min. 4 weeks old ■ Min. substrate temperature +10°C ■ Max. substrate temperature +30°C ■ Substrate temperature must be at least 3°C above dew point ■ Maximum relative air humidity 80% <p>For aesthetic purposes, always apply minimum of two coats.</p> <p>The degree of gloss of the applied material is influenced by environmental temperature, relative humidity and absorbency of the substrates.</p> <p>Prevent formation of puddles during Sikafloor application.</p>

Health and Safety information

Ecology	In liquid state the product contaminates water and should not get into drains, water and soils.
Disposal	In any case remnants of cleaning water and material must be removed according to local regulations.
Transportation	Non Hazardous
Important notes	<p>The product does not fall under the dangerous goods regulations. During application in closed rooms, pits and shafts etc, sufficient ventilation must be provided.</p> <p>Wear gloves and goggles during application</p>

Disclaimer	<p><i>The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.</i></p>
-------------------	--



Sika Limited (Vietnam)
 Nhon Trach 1 Industrial Zone,
 Nhon Trach Dist., Dong Nai Province
 Tel: (84-61) 3560 700 Fax: (84-61) 3560 699
 www.sika.com.vn, sikavietnam@vn.sika.com

